

USSN: 10/760,326

Response to Office Action Dated 04/17/2006

RECEIVED
CENTRAL FAX CENTER
SEP 18 2006AMENDMENTS TO THE CLAIMS

1. (currently amended) A resin composition comprising a polymer and at least 5% by weight of an ester compound, wherein the ester compound and the polymer are obtained by reacting a diene, a dienophile and a rosin acid in the presence of a disproportionation agent, wherein the dienophile is an aromatic vinylic hydrocarbon carboxylic acid.
2. (original) A resin composition according to claim 1 comprising at least 10% by weight of the ester compound.
3. (original) A resin composition according to claim 1, wherein the polymer has no acid functionalities.
4. (original) A resin composition according to claim 1, wherein the ester compound and the polymer are obtained by reacting a diene, a dienophile and a carboxylic acid present in a reaction mixture, wherein the reaction mixture comprises up to about 75% by weight of the diene, up to about 55% by weight of the dienophile, and from about 10 to about 75% by weight of the carboxylic acid.
5. (original) A resin composition according to claim 4, wherein the reaction mixture comprises from about 15 to about 60% by weight of the diene, from about 10 to about 45% by weight of the dienophile, and from about 15 to about 60% by weight of the carboxylic acid.
6. (original) A resin composition according to claim 1, wherein the resin composition has an acid number below about 50.
7. (original) A resin composition according to claim 1, wherein the resin composition has an acid number below about 20.
8. (cancelled)

USSN: 10/760,326

Response to Office Action Dated 04/17/2006

9. (cancelled)

10. (original) A resin composition according to claim 1, wherein the diene is a hydrocarbon diene.

11. (original) A resin composition according to claim 10, wherein the diene is a cyclic hydrocarbon diene.

12. (original) A resin composition according to claim 11, wherein the diene is a polycyclic hydrocarbon diene.

13. (original) A resin composition according to claim 12, wherein the diene is dicyclopentadiene.

14. (cancelled)

15. (cancelled)

16. (currently amended) A resin composition according to claim 1 ~~15~~, wherein the dienophile is styrene.

17. (currently amended) A resin composition comprising a polymer and at least 5% by weight of an ester compound, wherein the ester compound and the polymer are obtained by reacting a polycyclic hydrocarbon diene, a dienophile and a rosin acid, ~~a derivative of a rosin acid or a mixture of rosin acids thereof~~, wherein the dienophile is an aromatic vinylic hydrocarbon, and wherein the resin composition has an acid number below about 50.

18. (cancelled)

19. (cancelled)

USSN: 10/760,326

Response to Office Action Dated 04/17/2006

20. (currently amended) A resin composition according to claim 17, wherein the ester compound and the polymer are obtained by reacting ~~a diene, a dienophile and either a rosin acid, a derivative of a rosin acid, or a mixture thereof, present in a reaction mixture, wherein the reaction mixture comprises~~ up to about 75% by weight of the diene, up to about 55% by weight of the dienophile, and from about 10 up to about 75% by weight of the rosin acid, ~~the derivative of a rosin acid, or the mixture thereof.~~

21. (original) A resin composition comprising at least 5% by weight of an ester compound, and a polymer, wherein the ester compound and the polymer are obtained by reacting a polycyclic hydrocarbon diene, styrene and a rosin acid, ~~a derivative of a rosin acid or a mixture of rosin acids thereof.~~

22. (currently amended) An adhesive composition comprising a the resin composition of claim 1, ~~wherein the resin composition comprises at least 5% by weight of an ester compound, the resin composition also comprises a polymer, wherein the ester compound and the polymer are obtained by reacting a diene, a dienophile and a carboxylic acid.~~

23. (original) An adhesive composition according to claim 22, which is an aqueous pressure sensitive adhesive composition.

24. (original) An adhesive composition according to claim 22, which is a hot melt pressure sensitive adhesive composition.

25. (original) An adhesive composition according to claim 22, which is a flooring pressure sensitive adhesive composition.

26. (currently amended) A method for producing a resin composition which comprises providing a reaction mixture comprising up to about 75% by weight of a diene, up to about 55% by weight of a dienophile, wherein the dienophile is an aromatic vinylic hydrocarbon, and from about 10 to about 75% by weight of a ~~carboxylic~~ rosin acid, heating the reaction mixture at a

USSN: 10/760,326

Response to Office Action Dated 04/17/2006

temperature from about 175 °C. up to about 310 °C. for about 1 up to about 2 hours.

27. (currently amended) A method for producing a resin composition according to claim 26, wherein the reaction mixture comprises from about 15 to about 60% by weight of a diene, from about 10 to about 45% by weight of a dienophile, and from about 15 to about 60% by weight of a ~~carboxylic~~ rosin acid.

28. (cancelled)

29. (cancelled)

30. (cancelled)